


130R

TÊ DE REDUÇÃO, RANHURADO

REDUCING TEE, GROOVED



INFORMAÇÃO TÉCNICA - TECHNICAL INFORMATION

COD.	Tubo de Aço Steel tube			Máxima Pressão Serviço Maximum working pressure			Dimensões aprox. Approx. dimensions		Peso aprox. Weight approx. (kg)
	DN	INCHES	Ø ext (mm)	Bar	MPa	PSI	L1 (mm)	L2 (mm)	
613002/585	50x25	2"x1"	60,3x33,7	34,50	3,45	500	70	70	0,757
613002/587	50x40	2"x1 1/2"	60,3x48,3	34,50	3,45	500	70	70	0,794
613002/586	65x32	2 1/2"x1 1/4"	76,1x42,4	34,50	3,45	500	76	76	1,347
613002/587	65x40	2 1/2"x1 1/2"	76,1x48,3	34,50	3,45	500	76	76	1,332
613002/588	65x50	2 1/2"x2"	76,1x60,3	34,50	3,45	500	69	76	1,356
613002/5A5	80x25	3"x1"	88,9x33,7	34,50	3,45	500	108	108	2,388
613002/5A6	80x32	3"x1 1/4"	88,9x42,4	34,50	3,45	500	86	86	1,646
613002/5A7	80x40	3"x1 1/2"	88,9x48,3	34,50	3,45	500	86	86	1,652
613002/5A8	80x50	3"x2"	88,9x60,3	34,50	3,45	500	86	86	1,679
613002/5AB	80x65	3"x 2 1/2"	88,9x76,1	34,50	3,45	500	86	86	1,846
613002/5C7	100x40	4"x 1 1/2"	114,3x48,3	34,50	3,45	500	101	101	2,670
613002/5C8	100x50	4"x2"	114,3x60,3	34,50	3,45	500	101	101	2,685
613002/5CB	100x65	4"x 2 1/2"	114,3x76,1	34,50	3,45	500	101	101	2,854
613002/5CA	100x80	4"x3"	114,3x88,9	34,50	3,45	500	101	101	2,858
613002/5HC	125x100	5"x4"	139,7x114,3	34,50	3,45	500	124	124	4,882
613002/5K8	150x50	6 1/2" O.D x2"	165,1x60,3	20,70	2,07	300	140	140	6,293
613002/5KB	150x65	6 1/2" O.D x2 1/2"	165,1x76,1	20,70	2,07	300	140	140	6,448
613002/5KA	150x80	6 1/2" O.D x3"	165,1x88,9	20,70	2,07	300	140	140	6,484
613002/5KC	150x100	6 1/2" O.D x4"	165,1x114,3	20,70	2,07	300	140	140	6,562
613002/5KH	150x125	6 1/2" O.D x5"	165,1x139,7	20,70	2,07	300	140	140	6,882
613002/5E8	150x50	6"x2"	168,3x60,3	34,50	3,45	500	140	140	6,634
613002/5EB	150x65	6"x2 1/2"	168,3x76,1	34,50	3,45	500	140	140	6,334
613002/5EA	150x80	6"x3"	168,3x88,9	34,50	3,45	500	140	140	6,825
613002/5EC	150x100	6"x4"	168,3x114,3	34,50	3,45	500	140	140	6,904
613002/5EH	150x125	6"x5"	168,3x139,7	20,70	2,07	300	140	140	7,205
613002/5MA	200x80	8"x3"	219,1x88,9	34,50	3,45	500	175	175	12,218
613002/5MC	200x100	8"x4"	219,1x114,3	34,50	3,45	500	175	175	12,553
613002/5MH	200x125	8"x5"	219,1x139,7	20,70	2,07	300	175	175	12,542
613002/5NE	250x150	10"x6"	273,0x168,3	20,70	2,07	300	229	229	27,615

2/5 - 2= Vermelho - Red - 5= Galvanizado - Galvanized

Rev.3-09.21

1/2



Polígono Industrial ATUSA - Agurain S/N - 01200 Salvatierra (Alava) España
Tel.: (+34) 945 18 00 00 Fax : (+34) 945 30 01 53 e-mail: ventas@atusagroup.com
www.atusagroup.com





CARACTERÍSTICAS BÁSICAS

- Corpos fabricados em fundição nodular s/ASTM A536 (65-45-12).
 - * Mínima Tensão Rotura: 448 MPa (65.000 psi, 448 N/mm²).
 - * Limite Elástico mínimo: 310 MPa (45.000 psi, 310 N/mm²).
 - * Alongamento mínimo: 12%.
- Acabamento vermelho RAL3000 (pintura isenta de Chumbo) ou Galvanizado por imersão a quente s/ASTM A153.
- Porcas e parafusos em aço ao carbono s/ASTM A183 electrozincados s/ ASTM B633.

CONDIÇÕES DE TRABALHO ADMISSÍVEIS

- Pressão de serviço: ver tabela acima (os valores são reduzidos em 50% para ranhuras tipo conformação).
- Todas as instalações devem cumprir os valores P-T segundo os requisitos legais especificados. Em qualquer caso deve ser verificada, antes da sua colocação em serviço, a resistência dos Acessórios à acção das substâncias com as que entram em contacto (directo ou indirecto) de forma a que não possam deteriorar-se nas condições de uso.

Observações:

Dada a complexidade, variedade e grande quantidade de especificações particulares de cada instalação, em conjunção com a existência de diversos factores que podem afectar as condições de trabalho e natureza do produto, é da responsabilidade do utilizador final realizar os ensaios necessários para garantir o correcto funcionamento do produto em cada aplicação concreta.

A instalação do produto deverá ser realizada e mantida seguindo os códigos de boa prática e/ou normas existentes.

APLICAÇÕES GERAIS

- Apto para tubos de aço com e sem costura.
- Instalações de AQS.*
- Instalações de ÁGUA FRIA POTÁVEL.*
- Instalações de Segurança Contra Incêndios.
- Instalações de Ar Comprimido (isentas de hidrocarbonetos), Instalações Industriais, Rega e Maquinaria.
- Não válido para fluidos combustíveis, líquidos inflamáveis, gases explosivos e óleos vegetais/minerais.
- * Apenas produto galvanizado.

Nota 1: Dependendo da natureza química da água AQS, as superfícies galvanizadas podem sofrer algum grau de corrosão. Esta circunstância deve ser avaliada pelo responsável da instalação. A ATUSA não se responsabiliza pelas possíveis consequências adversas que possam ocorrer.

Nota 2: O uso em condições diferentes das aqui especificadas requer uma consulta prévia à ATUSA no momento da encomenda.

VANTAGENS

- Auto-centragem na tubagem.
- Fácil substituição de uniões e tubos.
- Embalagem versátil.
- Produto 100% Reciclável.

BASIC FEATURES

- Housing manufactured in ductile cast iron acc. ASTM A536 (65-45-12).
 - * Minimum Tensile Strength: 448 MPa (65.000 psi, 448 N/mm²).
 - * Minimum Yield Strength: 310 MPa (45.000 psi, 310 N/mm²).
 - * Elongation min: 12%.
- Red paint RAL3000 (non-lead) or Hot dip zinc Galvanizing acc. ASTM A153.
- Bolts and Nuts in carbon steel acc. ASTM A183 zinc electroplated acc ASTM B633.

PERMISSIBLE WORKING CONDITIONS

- Working pressure: see above table (values are reduced by 50% for rolled grooves).
- All installations has to meet the P-T values specified in the legal requirements. In any case has to be verified, before commissioning, the resistance of the Fittings to the action of the substances which they come into contact (direct or indirect) so that they cannot deteriorate in the conditions of use.

Remarks:

Due to the complexity, variety and large number of particular specifications for each installation, along with the existence of diverse factors which can affect the working conditions and nature of the product, it is the responsibility of the end-user to carry out the necessary tests to ensure the proper functioning of the product in any specific application.

Product installation must be carried out and maintained following the good practice codes and/or updated technical standards.

GENERAL APPLICATIONS

- Suitable for steel tubes (welded and not welded).
- Sanitary water systems.*
- COLD DRINKING WATER Installations.*
- Fire Fighting Installations.
- Pressured air pipe works (hydrocarbons free), Industrial installations, Irrigation and Machinery.
- Not valid for applications involving combustible fluids, flammable liquids, explosive gases, vegetal/mineral oils.
- * Only hot dip zinc galvanized products.

Note 1: Depending on chemical nature of HWS water, galvanized surfaces may suffer certain corrosion grade. This circumstance must be evaluated by the installation responsible. ATUSA is not responsible for the possible adverse consequences that may occur.

Note 2: Reference shall be made in case of use in conditions other than those here specified and requires prior consultation to ATUSA at order time.

ADVANTAGES

- Self-Centring on pipes.
- Easy substitution of couplings and tubes.
- Great packing versatility.
- Product 100% Recyclable.

AVISO Importante : não modificar nem eliminar nenhum componente da instalação sem primeiro ter despressurizado e drenado completamente o circuito, caso contrário podem resultar graves danos pessoais e/ou materiais.

Important NOTICE : never remove or modify any piping component without first de-pressurizing and draining completely the installation. Failure to do it could result in serious personal injury and/or economical losses.

Nota : Devido ao constante desenvolvimento dos nossos produtos, o desenho e os dados fornecidos podem ser alterados sem aviso prévio.

Nota : Due to the continuous development of our products, specifications may be changed without notification at any time.

Rev.3-09.21
2/2